PATENT ABSTRACTS OF JAPAN

(11)Publication number:

58-049408

(43)Date of publication of application: 23.03.1983

(51)Int.CI.

B01D 13/04

9/28 C08J

// B32B 5/18

(21) Application number: 56-148619

(71)Applicant:

NITTO ELECTRIC IND CO

(22) Date of filing:

19.09.1981

(72)Inventor:

TADA NAOKI

NAKAGOME KEISUKE KAMIYAMA YOSHIYASU MURAKITA RYUICHI

(54) MANUFACTURE OF SEMIPERMEABLE MEMBRANE

(57) Abstract:

PURPOSE: To obtain a semipermeable membrane free from membrane defect, high in water permeability, and strong in adhesion to a base, by coating solns. of polymers different from each other in viscosity on the porous base separately, and forming a membrane by solidifying them.

CONSTITUTION: A 10W40 soln. of a first polymer having 1.5W500 poise viscosity at 30°C is coated on a woven or nonwoven fabric made of polyester, polypropylene, polyethylene fibers or the like, and a second polymer soln. lower in viscosity and concn. than the first soln. is coated on the first soln. being kept in a uniform soln. state, and then, the solns. are solidified to form a membrane, thus permitting the porous base having a prescribed gas permeability to be coated with the first polymer soln. having high viscosity and high concn., and properly penetrated into the base, the unevenness of the base surface to be covered, defects such as pinholes to be prevented, and therefore, a semipermeable membrane having a uniform surface and strong adhesion to the membrane and the base to be obtained.

LEGAL STATUS

[. e of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2000 Japan Patent Office